



Erosion Control Blanket

Standard Netting – Double Net – 100% Coconut (SDNC)

The BMP Standard Double Net Coconut (SDNC) Erosion Control Blanket is made of two synthetic nets and filled with 100% coconut fiber, designed for use on slope and channel applications. These long-term blankets are designed to reduce soil erosion and channel sedimentation through a combination of physical and biological means. The Blanket provides an effective and cost-efficient solution to soil erosion and sedimentation control. These blankets also offer a protective vegetative cover that aids in reducing water velocity and sedimentation.

Tested Property

Tested Method

Tested Results

Netting		Top and Bottom (Double) Photodegradable Net
Fill		100% Coconut
Longevity		Long Term - est. 36 months
Mass Per Unit Area	ASTM D6475	9.50 oz/sq/yd 323 g/m ²
Tensile Strength	ASTM D6818	MD - 14.9 lb/in @ % 21.3 XD - 16.9 lb/in @ % 20.7
Thickness	ASTM D6525	0.251 in 0.637 cm
Light Penetration/Ground Cover	ASTM D6567	18.4%
Water Absorption	ASTM D1117	207%
Unvegetated Bench-Scale Rain Splash and Runoff	ASTM D7101	50 mm (2 in.) / hr for 30 min. Soil Loss Ratio† = 39.68 C Factor: 0.025 100 mm (4 in.) / hr for 30 min. Soil Loss Ratio† = 36.12 C Factor: 0.028 150 mm (6 in.) / hr for 30 min. Soil Loss Ratio† = 42.93 C Factor: 0.023
Unvegetated Bench-Scale Shear Stress	ASTM D7207	2.80 psf @ ½ in soil loss
Seed Germination and Plant Growth Under Bench-Scale Conditions	ASTM D7322	% of Average Control = 253% - PASS % of Concurrent Control = 251% - PASS

† Soil Loss Ratio = Soil Loss Bare Soil / Soil Loss with RECP = 1 / C-Factor (Note: soil loss is based on regression analysis)

Roll Dimensions

BMP-SDNC08	8' x 112.5' (100sy / 83.6127 m ²) - ~50 lbs	25 Rolls/Pallet
BMP-SDSNC16	16' x 112.5' (200sy / 167.23 m ²) - ~100 lbs	20 Rolls/ Pallet
BMP-SDNC08JR	8' x 562.5' (500sy / 418.06 m ²) - ~250 lbs	4 Rolls/ Pallet
BMP-SDNSC08JR	16' x 562.5' (1000sy / 836.13 m ²) - ~500 lbs	4 Rolls/ Pallet



Shipping From:

#50-183073 RR 150,
Brooks, Alberta T0J 2A0
Canada, County of Newell

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for the accuracy and reliability of said information or the performance of any product. Any specification, property or application listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.